

## Technical data – NYROSTEN T 55-13-20510, fluid

The technical data are not specifications. They represent mean values and do not guarantee specific characteristics.

### NYROSTEN T 55-13-20510, fluid

CHARACTERISTIC	TEST STANDARD	VALUE
Color		green-brown
Flash Point	DIN 51 755	> 65 °C
Consistency		fluid
Solvent content		50%
Processing		spraying

### CHARACTERISTICS AFTER THE SOLVENT EVAPORATES

CHARACTERISTIC	TEST STANDARD	VALUE
Consistency		elastic
Drop point	ISO 2176	> 80 °C
Drop point	DIN 51801/2	> 100 °C
Penetration	ISO 2137	80 - 130 1/10 mm
Flash Point	DIN ISO 2592	> 220 °C
Breaking point (Application thickness 75g/m <sup>2</sup> )	DIN EN 12593	- 40 °C

### INITIAL ANTI-CORROSION PROTECTION

NYROSTEN T 55-13-20510

### SPECIAL FEATURE

Usable for rope-cores and as post impregnation

### DELIVERY OPTIONS

500 ML AEROSOL CAN

5 KG CAN

10 KG PAIL

25 KG HOBBOCK

200 KG BARREL



\*

\* Drum

Explanation of symbols on page 2

As we put great value on advisory service and enjoy carrying out expert talks, please contact us directly if you need further information (+49(0)2831 - 9245-6).